



013 LUPA® TWIST



### APPLICATIONS

DOCK LINE  
TOWING LINE  
ANCHOR LINE

### SPECIFICATIONS

MATERIAL	100% HT POLYAMIDE FIBER
TYPE	A
SPECIFIC GRAVITY	1,14 KG/DM <sup>3</sup>
CONSTRUCTION	3 STRAND PLAITED
UV RESISTANCE	VERY GOOD
CHEMICAL RESISTANCE	GOOD
MELTING POINT	218°C
CRITICAL TEMPERATURE	130°C
ELONGATION AT BREAK	APPROX.%30-35
FIBER WATER ABSORPTION	APPROX. %3-4
WET ABRASION	SUFFICIENT
DRY ABRASION	GOOD
COLOUR	WHITE-NAVY BLUE-BLACK
STANDARD	EN ISO 1140
LENGTH	100-200 M PLASTIC/WOODEN SPOOL OR COIL

OTHER COLOURS ON REQUEST



### BENEFITS / FEATURES

DOES NOT HARDEN  
SOFT HAND  
DURABLE  
HIGH BREAKING LOAD  
EXCELLENT SHOCK ABSORPTION  
EASY TO SPLICE

ART.NO	DIA	WEIGHT	B.LOAD
	(Ø)	(kg / 100 m)	(kgf)*
013	4	0,98	380
013	5	1,54	570
013	6	2,22	810
013	8	3,95	1.420
013	10	6,17	2.160
013	12	8,88	3.060
013	14	12,10	4.250
013	16	15,80	5.280
013	18	20,00	6.875
013	20	24,70	8.500
013	22	29,90	10.250
013	24	35,50	12.000
013	26	41,70	14.500
013	28	48,40	17.000
013	30	55,50	19.000
013	32	63,20	21.125
013	36	80,00	27.500
013	40	98,70	34.000
013	48	142,00	48.000
013	56	193,00	68.000
013	64	253,00	84.500

\*UNSPliced BREAK LOAD (ALL TESTS ARE IN ACCORDANCE WITH ISO 2307)

