




005 - 505 DYNE K® 78 / 99



APPLICATIONS

SPI POLE UPHAUL
SPI POLE FOREGUY
BACKSTAYS
VANG
CUNNINGHAM
MAIN OUTHAUL


SPECIFICATIONS

MATERIAL	COATED DYNEEMA® SK 78/99
SPECIFIC GRAVITY	0,97 KG/DM ³
CONSTRUCTION	12 STRAND BRAIDED
UV RESISTANCE	EXCELLENT
CHEMICAL RESISTANCE	EXCELLENT
MELTING POINT	147°C
CRITICAL TEMPERATURE	65°C
WORKING STRETCH	<1%
FIBER WATER ABSORPTION	NONE
WET ABRASION	EXCELLENT
DRY ABRASION	EXCELLENT
STANDARD	ISO 10325
LENGTH	100-200 M ORANGE SPOOL OR COIL

OTHER COLOURS & LARGER DIAMETERS UPON REQUEST

ART.NO	DIA (Ø)	WEIGHT (kg / 100 m)	B. LOAD (kgf)*	
			SK78 (ART.NO: 005)	SK99 (ART.NO: 505)
005 - 505	2	0,28	425	502
005 - 505	3	0,62	950	1.121
005 - 505	4	1,05	1.650	1.947
005 - 505	5	1,60	2.600	3.068
005 - 505	6	2,30	3.750	4.425
005 - 505	8	4,00	6.600	7.788
005 - 505	10	6,10	10.400	12.272
005 - 505	12	8,70	15.000	17.700
005 - 505	14	11,70	20.400	24.072
005 - 505	16	15,10	26.520	31.294
005 - 505	18	19,00	31.620	37.312
005 - 505	20	23,20	38.760	45.737
005 - 505	22	28,10	45.900	54.162
005 - 505	24	33,10	53.000	62.540

*UNSPliced BREAK LOAD (ALL TESTS ARE IN ACCORDANCE WITH ISO 2307)



BENEFITS / FEATURES

SUPERIOR ABRASION RESISTANCE
EXCELLENT BREAKING LOAD (SK99)
BUOYANT
DURABLE
VERY LOW STRETCH
LIGHTWEIGHT
EASY TO SPLICE
DOES NOT KINK

Dyneema®

