



018 LUPP® SQUARE


BENEFITS / FEATURES

ECONOMICALLY PRICED
EASY TO SPLICE
EXCELLENT GRIP
DOES NOT KINK
BUOYANT
MODERATE ELONGATION

APPLICATIONS

VESSEL SECONDARY MOORING LINES

SPECIFICATIONS

MATERIAL	100% HT POLYPROPYLENE FIBER
TYPE	L
SPECIFIC GRAVITY	0,91 KG/DM ³
CONSTRUCTION	8 STRAND PLAITED (4X2)
UV RESISTANCE	SUFFICIENT
CHEMICAL RESISTANCE	VERY GOOD
MELTING POINT	165°C
CRITICAL TEMPERATURE	80°C
ELONGATION AT BREAK	APPROX.%23
FIBER WATER ABSORPTION	NONE
WET ABRASION	SUFFICIENT
DRY ABRASION	SUFFICIENT
COLOUR	BLACK - WHITE - NAVY BLUE
STANDARD	EN ISO 1346
LENGTH	100-200 M ORANGE SPOOL OR COIL

OTHER COLOURS UPON REQUEST

ART.NO	DIA (mm)	WEIGHT (kg / 100 m)	B.LOAD * (kgf)
	(Ø)		
018	8	2,90	1.080
018	10	4,52	1.625
018	12	6,51	2.265
018	14	8,86	3.225
018	16	11,60	4.310
018	18	14,60	5.350
018	20	18,10	6.500
018	22	21,90	7.740
018	24	26,00	9.060
018	26	30,60	10.500
018	28	35,40	12.900
018	30	40,70	14.600
018	32	46,30	16.400
018	36	58,60	20.100
018	40	72,30	24.300
018	48	104,00	33.700
018	56	142,00	44.600
018	64	185,00	56.800
018	72	234,00	70.200
018	80	289,00	86.000
018	88	350,00	102.000
018	96	417,00	120.000

*UNSPliced BREAK LOAD (ALL TESTS ARE IN ACCORDANCE WITH ISO 2307)

