

LUPA® ROUND



216 LUPA® ROUND



APPLICATIONS

DOCK LINE
ANCHOR LINE
TOWING LINE

SPECIFICATIONS

MATERIAL	100% HT POLYAMIDE FIBER
TYPE	T
SPECIFIC GRAVITY	1,14 KG/DM ³
CONSTRUCTION	12 STRAND BRAIDED
UV RESISTANCE	VERY GOOD
CHEMICAL RESISTANCE	GOOD
MELTING POINT	218°C
CRITICAL TEMPERATURE	130°C
ELONGATION AT BREAK	APPROX. %30-35
FIBER WATER ABSORPTION	APPROX. %3-4
WET ABRASION	SUFFICIENT
DRY ABRASION	GOOD
COLOUR	WHITE-NAVY BLUE-BLACK
STANDARD	EN ISO 1141
LENGTH	100-200 M WOODEN SPOOL OR COIL

OTHER COLOURS ON REQUEST



BENEFITS / FEATURES

DOES NOT HARDEN
DOES NOT KINK
SOFT HAND
DURABLE
HIGH BREAKING LOAD
EXCELLENT SHOCK ABSORPTION
EASY TO SPLICE

ART.NO	DIA	WEIGHT	B.LOAD
	(Ø)	(kg/100 m)	(kgf)*
216	20	25,00	8.670
216	22	30,50	10.300
216	24	36,00	12.030
216	26	42,50	14.500
216	28	49,00	17.000
216	30	56,00	19.000
216	32	64,00	21.125
216	34	72,50	24.310
216	36	81,00	27.500
216	38	90,50	30.750
216	40	100,00	34.000
216	42	110,50	37.500
216	44	121,00	41.000
216	46	132,50	44.500
216	48	144,20	48.000
216	52	170,00	58.000
216	56	197,00	68.000
216	60	226,00	76.250
216	64	257,00	84.500
216	72	325,00	110.000
216	80	401,00	129.000
216	88	486,00	152.000
216	96	578,00	183.000

*UNSPliced BREAK LOAD (ALL TESTS ARE IN ACCORDANCE WITH ISO 2307)

